

TASETO 不锈钢 MIG 焊丝

牌号	符合的型号		化学				
	JIS	AWS	C	Si	Mn	P	S
MG308	YS308	ER308	≤ 0.08	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG308H*	YS308H	ER308H	0.04~0.08				
MG308L	YS308L	ER308L	≤ 0.03	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
			≤ 0.020				
			≤ 0.010				
MG308LSi	YS308LSi	ER308LSi	≤ 0.03	0.65~1.00			
MG309	YS309	ER309	≤ 0.12	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG309LSi	YS309LSi	ER309LSi	≤ 0.03	0.65~1.00			
MG309L	YS309L	ER309L	≤ 0.03	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG310	YS310	ER310	0.08~0.15	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG310S	YS310S	—	≤ 0.08	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG316	YS316	ER316	≤ 0.08	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG316L	YS316L	ER316L	≤ 0.03	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
			≤ 0.020				
			≤ 0.010				
MG316LSi	YS316LSi	ER316LSi	≤ 0.03	0.65~1.00			
MG317L	YS317L	ER317L	≤ 0.03	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG347	YS347	ER347	≤ 0.08	≤ 0.65	1.0~2.5	≤ 0.03	≤ 0.03
MG347HT	YS347	ER347	0.04~0.08	0.65~1.00			
MG329J3L*	YS2209	ER2209	≤ 0.03	≤ 0.90	0.5~2.0	≤ 0.03	≤ 0.03
MG329J4L*	YS329J4L	ER2594	≤ 0.03	≤ 0.90	0.5~2.5	≤ 0.03	≤ 0.03

※表示订货后生产的品种。

认证/NK,ABS(有 MG308L, MG309, MG316L 三个牌号)

成分(%)					用途
Ni	Cr	Mo	Cu	其他	
9.0~11.0	19.5~22.0	≤0.75	≤0.75	—	SUS304 用
		≤0.50			
9.0~11.0	19.5~22.0	≤0.75	≤0.75	—	SUS304L 用
12.0~14.0	23.0~25.0	≤0.75	≤0.75	—	SUS309 用, 与碳钢 异材焊接用
12.0~14.0	23.0~25.0	≤0.75	≤0.75		
20.0~22.5	25.0~28.0	≤0.75	≤0.75	—	SUS310S 用
20.0~22.5	25.0~28.0	≤0.75	≤0.75	—	SUS310S 用
11.0~14.0	18.0~20.0	2.0~3.0	≤0.75	—	SUS316 用
11.0~14.0	18.0~20.0	2.0~3.0	≤0.75	—	SUS316L 用
13.0~15.0	18.5~20.5	3.0~4.0	≤0.75	—	SUS317 用
9.0~11.0	19.0~21.5	≤0.75	≤0.75	Nb=10×C%~1.0	SUS321,347 用
7.5~9.5	21.5~23.5	2.5~3.5	≤0.75	N=0.08~0.20	SUS329J3L 用
8.0~11.0	23.0~27.0	3.0~4.5	≤0.75	N=0.08~0.30	SUS329J4L 用