





Water displacement type antirust lubricant oil VISTOHL E

VISTOHL E is dehydration anti-rust oil, capable of water displacement and anti-fingerprint. Also have excellent lubricant effect.

- Recommended Use: Make it easy to loosen rusted screw or bolt, rust prevention, dehumidification, degreasing etc.
- Feature and the comparison with other commercial brand.

<p>【Excellent water displacement】 Spray each antirust oil directly to the water-wetted cast steel plate, and after two days.</p>	<p>【Good wetting and spreading ability】 Drip one drop of each oil, measure the spreading area after 5 min.</p>																												
 <p>VISTOHL E Sample A Sample B</p>	 <table border="1"> <caption>Spreading Diameter (mm) vs Time (min)</caption> <thead> <tr> <th>Time (min)</th> <th>VISTOHL E (mm)</th> <th>Sample A (mm)</th> <th>Sample B (mm)</th> </tr> </thead> <tbody> <tr> <td>0</td> <td>15</td> <td>14</td> <td>14</td> </tr> <tr> <td>1</td> <td>22</td> <td>21</td> <td>19</td> </tr> <tr> <td>2</td> <td>27</td> <td>27</td> <td>23</td> </tr> <tr> <td>3</td> <td>34</td> <td>32</td> <td>26</td> </tr> <tr> <td>4</td> <td>40</td> <td>36</td> <td>29</td> </tr> <tr> <td>5</td> <td>47</td> <td>39</td> <td>31</td> </tr> </tbody> </table>	Time (min)	VISTOHL E (mm)	Sample A (mm)	Sample B (mm)	0	15	14	14	1	22	21	19	2	27	27	23	3	34	32	26	4	40	36	29	5	47	39	31
Time (min)	VISTOHL E (mm)	Sample A (mm)	Sample B (mm)																										
0	15	14	14																										
1	22	21	19																										
2	27	27	23																										
3	34	32	26																										
4	40	36	29																										
5	47	39	31																										
<p>【Excellent rust prevention effect】 Apply various antirust oil, then spray salt water every hour, after 3 days</p>	<p>【Good workability】 One-touch nozzle, capable of all position spray</p>																												
 <p>VISTOHL E Sample A Sample B</p>																													

- Lubricity test (Power need to loosen rusted-bolt)

○BLANK : 35kgf·cm,

○Application of VISTOHL E : 2.6kgf·cm